

KENTHERM 180DGL (SID/GL)



KETHERM 180 DGL SiD/GL 10 mm²

KENTHERM

Technische Daten

- Spezial-Silicon-Einzeldadern mit erhöhter Wärmebeständigkeit in Anlehnung an DIN VDE 0250 Teil 1 und Teil 502
- **Temperaturbereich**
-60° C bis +180° C (kurzzeitig +220°C)
- Grenztemperatur am Leiter, im Betrieb + 180° C
- **Nennspannung** 500 V
- **Prüfspannung** 2000 V
- **Durchschlagsspannung** min. 5000 V
- **Mindestbiegeradius** 15x Leitungs \varnothing (SiD nur für feste Verlegung)
- **Strahlenbeständigkeit** Bis 20×10^6 cJ/kg (bis 20 Mrad)
- **Korrosivität von Brandgasen (Halogenfreiheit)**
Prüfung nach DIN VDE 0472 Teil 813 und IEC 60754-2
- **Brennverhalten**
keine Brandweiterleitung Prüfung nach VDE 0472 Teil 804 Prüfmeth B und IEC 60332-1

Kabelaufbau

Typ SiD

- CU- Litze verzinkt, massiv
- siliconisoliert
- SID/GL = SiD plus Glasseidengeflecht

Verwendung

Als spezielle hoch- bzw. niedertemperaturbeständige Leitung. Vor allem eingesetzt in Hütten-, Stahl- und Walzwerken, Gießereien, Flugzeug- und Schiffsbau, Zement-, Glas- und Keramikfabriken. Die Leitungen sind halogenfrei und eignen sich besonders zum Einsatz in Kraftwerken.

Beständig gegen

- hochmolekulare Öle
- pflanzliche und tierische Fette
- Alkohole
- Weichmacher und Clophenes
- verdünnte Säuren
- Laugen und Salzlösungen
- Oxidationsmittel
- tropische Einflüsse
- Seewasser
- Sauerstoff, Ozon

Hinweis

Bei fester Verlegung nur in offenen, belüfteten Rohrsystemen oder Kanälen zu verlegen. Ansonsten vermindern sich bei Luftabschluß in Verbindung mit Temperaturen über 90° C die mechanischen Eigenschaften von Silicon.

C€ = Das Produkt ist konform zur EG-Niederspannungsrichtlinie 73/23/EWG bzw. 93/68/EWG.

Technical data

Special silicone single cores with higher heat-resistance range adapted to DIN VDE 0250 part 1 and part 502

Temperature range -60°C to +180°C (up to +220°C for short time)

Temperature limit at the conductor in operation +180°C

Nominal voltage 500 V

Test voltage 2000 V

Minimum bending radius 15xcable \varnothing

(SiD only for permanent installation)

Radiation resistance

up to 20×10^6 cJ/kg (up to 20 Mrad)

Corrosiveness of combustion gases

(freedom from halogen)

test method to DIN VDE 0472 part 813 and IEC 60754-2

Behaviour in fire no flame propagation

test method B to DIN VDE 0472 part 804 and IEC 60332-1

Cable structure

Typ SiD

- Tinned copper conductors , massive
- Silicon core insulation
- SID/GL = SiD plus glass braid

Application

Silicone single cores are special cables for use in high, resp. low temperature areas.

They are used mainly in the steel producing industries, in aviation industries as well as in ship building, cement, glass and ceramic factories. As this cables are halogen-free, especially suited for use in power stations.

Resistant to

- High molecular oils
- Fats for vegetables and animals
- Alcohols
- Plasticizers and clophenes
- Diluted acids
- Lyes and salt dissolution
- Oxidation substances
- Tropical influences and weather
- Lake water
- Oxygen and UV

Note

For laying as a fixed installation only in open or ventilated pipe systems as well as in ducts. Otherwise the mechanical properties of the silicon are reduced by the enclosed air at temperatures exceeding 90°.

KENTHERM 180 DGL SILIKON-Litze SiD/GL (-60°C bis +180°C)

Artikel-Nr.	Aderzahl x Querschnitt mm ²	ADM mm ca.	Gewicht kg/km ca.	CU-Zahl kg/km
Part number	no. Cores x cross section mm ²	Outer diameter approx. mm	weight approx. kg/km	Copper weight approx. kg/km
0110050DGL	0,50	2,50	10,00	4,80
0110075DGL	0,75	2,70	15,00	7,20
0110100DGL	1,00	2,80	19,00	9,60
0110150DGL	1,50	3,10	28,00	14,40
0110250DGL	2,50	3,70	40,00	24,00
0110400DGL	4,00	4,40	55,00	36,00
0110600DGL	6,00	4,90	80,00	58,00